



Puur floors limited
Bentinck House 3-8 Bolsover St.
London W1W 5BB

tel: 0207 118 9100
e: info@puurfloors.com
w: www.puurfloors.com

Specification Sheet

Puur PSR

Cementitious overlay flooring system

NBS category M – surface finishes

- Polymer modified cementitious screed
- Applied to sand / cement screed, levelling screed, concrete at less than 5% moisture content, stone slabs, ply (to spec) or interlocking cement board
- Colour: natural white pigmented to shade.

Application

- Sand or grind of local irregularities in the existing substrate
- Make good any defects, cracks in the substrate using approved methods
- Remove dust and debris
- Prime area to manufacturers instruction
- PSR mix to manufacturers instruction
- Allow 12 hour (or overnight cure period)
- Application of penetrating Puur seal
- Buff to satin finish

Installation Standard 6mm (nominal 4mm - maximum 12mm)

.....
Colour Natural white or pigmented with RAL or NCS base colours

.....
Slip resistance dry R12

.....
Slip resistance wet R11

Substrate

Flatness / surface regularity: Max permissible deviation SR2 generally