



Puur floors limited
Bentinck House 3-8 Bolsover St.
London W1W 5BB

tel: 0207 118 9100
e: info@puurfloors.com
w: www.puurfloors.com

Technical Data Sheet

Puur Microcrete

Cementitious overlay flooring system

Product Description

Decorative coloured layers of blended fillers, cement and polymers to achieve a polished look which in addition can be used on vertical surfaces.

Puur Microcrete is a high strength cement-based product and in common with all such products, can form hair line cracks to the surface during curing. Such cracking is purely aesthetic feature and does not detract from the floors performance. As with traditional concrete the final finish will vary in shade and patina across the surface. This variance is the decorative feature of the floor, the precise nature of which cannot be guaranteed, as is dependant on site conditions, i.e. temperature, humidity and application.

Detailed specification

- Finish: polished and sealed satin
- Substrate preparation: on screed by use of vacuum assisted diamond grinding equipment where appropriate
- Substrate preparation: on timber, by the use of vacuum assisted sanding equipment where appropriate
- P5 moisture resistant T&G or marine ply
- Other situations in accordance with Puur floors instructions
- Natural white or pigmented browns, putty's, greys and colours; NCS or RAL classic colours
- Mineral bonded – solvent free
- UV stable

Product application

The materials is manually applied by trowel with a total of 2-4 layers, which builds to an (optimal) thickness of 2-4 mm. The layers are sanded and finished with 2 Pu seal coats to achieve a water resistant, cleanable protective coating



Puur floors limited
Bentinck House 3-8 Bolsover St.
London W1W 5BB

tel: 0207 118 9100
e: info@puurfloors.com
w: www.puurfloors.com

Technical Data Sheet

Puur Microcrete

Cementitious overlay flooring system

Substrate requirements

Concrete must be structurally sound fully cured, ideally minimum 28 days old, flat smooth, clean and dry with adequate damp proof membrane installed. The design strength of the concrete should be minimum 25-30 N/mm², flexural tensile strength 1.2 N /mm², with moisture content at the time of installation not greater than 5%. Any holes, cracks, defects, to be repaired via approved methods.

Timber substrate normally 2 layers, each of 18mm tongue and groove approved moisture resistant chipboard or marine plywood installed in cross fashion for strength and rigidity with tight fully glued joints, fixed and counter sunk at 150mm centre along line of joints and additional areas where required, with suitable expansion provision around the perimeter of timber floor to wall. The installed timber surface is to be prepared by sanding to remove any impurities and impregnated with Puur specialist primer.

Interlocking cement board standard depths as available 20 -30mm

Compatible with wet or electric under floor heating, embedded in screed or covered with interlocking cement board.

Floor to dry/cure for minimum 24 hours for light foot traffic, careful mechanical loading after 48 hours, full chemical cure at 7 days based on ambient temperature of 20°C